



Metalon® Conductive Inks for Printed Electronics

www.novacentrix.com

Metalon® JS-A554

Aerosol Ink – Aqueous-based silver ink

(specifically formulated for printing with the NanoJet from IDS)

JS-A554 is an electrically conductive silver nanoparticle ink designed to produce conductive traces on substrates such as paper, PET, glass, and polyimide. **JS-A554** ink is specially formulated for aerosol printing using ultrasonic atomization with the NanoJet from IDS. The ink contains a polymeric additive for improved adhesion to glass and other substrates. Applications for the ink include high density interconnects and fine line printing.

RESISTIVITY - THERMAL PROCESSING			
Cure temperature (°C)	Cure time (minutes)	Volume Resistivity (Ω-cm)	x Bulk Silver
125	30	110 E-6	70
150	30	26.4 E-6	16.7
175	30	13.5 E-6	8.5
200	30	10.2 E-6	6.5
225	30	8.0 E-6	5.1
250	30	6.3E-6	4.0
275	30	4.2 E-6	2.7

- Data collected from drawdowns on Kapton HN using a #10 Meyer rod.
- Resistivity calculated using an estimated porosity of 25%

ADHESION PERFORMANCE	
SUBSTRATE	Crosshatch Rating
PET	5B
Kapton	5B
Glass	5B

Physical Properties	General Description Water-based Ag nanoparticle ink Viscosity 3 - 5 cP Specific Gravity 1.3 Flash Point Non-flammable Average dispersed particle size 35 nm Ag Content 25% w/w (Typical values reported)
Shipping and Packaging	Standard sample order is 50 mL or multiples of 50 mL. Inquire directly for packaging of larger quantities.

www.novacentrix.com
 Contact us today to learn more.
info@novacentrix.com

04/19/2024