




(86) Date de dépôt PCT/PCT Filing Date: 2009/03/25  
 (87) Date publication PCT/PCT Publication Date: 2010/04/22  
 (45) Date de délivrance/Issue Date: 2016/01/12  
 (85) Entrée phase nationale/National Entry: 2011/04/14  
 (86) N° demande PCT/PCT Application No.: US 2009/038289  
 (87) N° publication PCT/PCT Publication No.: 2010/044904  
 (30) Priorité/Priority: 2008/10/17 (US61/196,531)

(51) Cl.Int./Int.Cl. *C23C 18/52* (2006.01),  
*C09D 11/52* (2014.01)  
 (72) Inventeurs/Inventors:  
POPE, DAVE S., US;  
SCHRODER, KURT A., US;  
RAWSON, IAN M., US  
 (73) Propriétaire/Owner:  
NCC NANO, LLC, US  
 (74) Agent: KIRBY EADES GALE BAKER

(54) Titre : PROCEDE POUR REDUIRE DES FILMS MINCES SUR DES SUBSTRATS A BASSE TEMPERATURE  
 (54) Title: METHOD FOR REDUCING THIN FILMS ON LOW TEMPERATURE SUBSTRATES



(57) **Abrégé/Abstract:**

A method for producing an electrically conductive thin film on a substrate is disclosed. Initially, a reducible metal compound and a reducing agent are dispersed in a liquid. The dispersion is then deposited on a substrate as a thin film. The thin film along with the substrate is subsequently exposed to a pulsed electromagnetic emission to chemically react with the reducible metal compound and the reducing agent such that the thin film becomes electrically conductive.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
22 April 2010 (22.04.2010)

(10) International Publication Number  
**WO 2010/044904 A1**

- (51) International Patent Classification:  
C23C 18/00 (2006.01)
- (21) International Application Number:  
PCT/US2009/038289
- (22) International Filing Date:  
25 March 2009 (25.03.2009)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
61/196,531 17 October 2008 (17.10.2008) US
- (71) Applicant (for all designated States except US): NCC NANO, LLC [US/US]; Three Forest Plaza, Suite 930, 12221 Merit Drive, Dallas, TX 75250 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): POPE, Dave, S. [US/US]; 27 Florence Street, Andover, MA 01810 (US). SCHRODER, Kurt, A. [US/US]; 13501 Pfluger Berkman Lane, Coupland, TX 78615 (US). RAWSON, Ian, M. [US/US]; 601 Elmwood Place, Apt. #2, Austin, TX 78705 (US).
- (74) Agent: NG, Antony, P.; Dillon & Yudell LLP, 8911 N. Capital Of Texas Hwy., Suite 2110, Austin, TX 78759 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: METHOD FOR REDUCING THIN FILMS ON LOW TEMPERATURE SUBSTRATES




FIG. 1

(57) Abstract: A method for producing an electrically conductive thin film on a substrate is disclosed. Initially, a reducible metal compound and a reducing agent are dispersed in a liquid. The dispersion is then deposited on a substrate as a thin film. The thin film along with the substrate is subsequently exposed to a pulsed electromagnetic emission to chemically react with the reducible metal compound and the reducing agent such that the thin film becomes electrically conductive.

WO 2010/044904 A1

**WO 2010/044904 A1** 

---

**Published:**

— *with international search report (Art. 21(3))*

# **METHOD FOR REDUCING THIN FILMS ON LOW TEMPERATURE SUBSTRATES**

## **BACKGROUND OF THE INVENTION**

### **1. Technical Field**

The present invention relates to curing method in general, and, in particular, to a method for reducing thin films on low-temperature substrates.

### **2. Description of Related Art**

One approach to making electronic circuits is to print electrical conductors with metallic ink onto a substrate, and the substrate is then heated to sinter the particles of the metallic ink in order to form electrical conducting traces. Generally, most printed metals suitable for electrically conduction need to be heated to a very high temperature, often within a couple hundred degrees centigrade of their melting point, in order to sinter and become conductive.

Two of the most pursued elements for making conductive traces in printed electronics are silver and copper. Silver has two advantages over copper because silver can be heated in air with minimal oxidation and that its oxides, which are comparatively low in conductivity, decompose at relatively low temperatures. These two qualities, coupled with the fact that silver is the most electrically conductive metal often outweigh its high cost when making conductive traces. Thus, even though copper has about 90% of the conductivity of silver and it is usually 50-100 times cheaper on a mass basis, silver inks still dominate the printed electronics market because the additional cost of making and processing copper inks to avoid oxidation is generally higher than the difference in material costs.

It is well-known in the prior art that some metal oxides can be reduced by hydrogen or hydrocarbons at an elevated temperature if they have a positive reduction potential. For example, copper can be first extracted by mixing copper oxide bearing ore with charcoal along with an application of heat. When oxidized copper particles or even pure copper oxide is heated in the presence of a reducer, the oxidized copper particles can sinter to form a conductor.

When making thin film conductors by printing copper particles, a very conductive trace can be formed if the particles are heated to their sintering temperature in an inert or reducing atmosphere. Since the melting point of copper is nearly 1,085 °C, the temperature required for sintering dictates that only high temperature substrates such as glass or ceramic can be used. Such high-temperature requirement prevents the usage of inexpensive substrates such as paper or plastic.

Alternatively, if a copper particle film is deposited on a low-temperature substrate, it can be heated to near the substrate's decomposition temperature and then be placed in a reducing atmosphere, but the low temperature dramatically increases the amount of time needed for curing from seconds to minutes or even hours, depending on the thickness of the film and the temperature. At low temperatures, sintering is very limited,

and thus the film resistivity becomes high. Furthermore, the need for an inert or reducing atmosphere also dramatically increases processing cost. Thus, it would be desirable to provide an improved method for rapidly reducing metal oxide on low-temperature substrates in ambient atmosphere.

## SUMMARY OF THE INVENTION

In accordance with a preferred embodiment of the present invention, a reducible metal compound and a reducing agent are initially dispersed in a liquid, such as water. The dispersion is then deposited on a substrate as a thin film. The thin film along with the substrate is subsequently exposed to a pulsed electromagnetic emission to chemically react with the reducible metal compound and the reducing agent such that the thin film becomes electrically conductive.

All features and advantages of the present invention will become apparent in the following detailed written description.

In accordance with certain exemplary embodiments of the invention, there is provided a method for producing an electrically conductive thin film on a substrate, the method comprising: dispersing copper powder, ascorbic acid and glycerol in a liquid; depositing the dispersion on a non-conductive substrate as a thin film; and exposing the thin film along with the substrate to a pulsed electromagnetic emission in an ambient atmosphere to chemically react the copper powder and the ascorbic acid and glycerol to render the thin film electrically conductive.

In accordance with further exemplary embodiments of the invention, there is provided a method for reducing thin films on low-temperature substrates, the method comprising: dispersing copper sulphate in a first liquid; dispersing ascorbic acid and glycerol in a second liquid; depositing the first and second dispersions on a non-conductive substrate as a thin film; and exposing the thin film along with the substrate to a pulsed electromagnetic emission in an ambient atmosphere in order to initiate a redox reaction between the copper sulphate and the ascorbic acid and glycerol on the substrate.

## **BRIEF DESCRIPTION OF THE DRAWINGS**

The invention itself, as well as a preferred mode of use, further objects, and advantages thereof, will best be understood by reference to the following detailed description of an illustrative embodiment when read in conjunction with the accompanying drawings, wherein:

Figure 1 is a flow diagram of a method for curing a thin film on a low-temperature substrate, in accordance with a preferred embodiment of the present invention; and

Figure 2 is a diagram of a curing apparatus, in accordance with a preferred embodiment of the present invention.

## DETAILED DESCRIPTION OF A PREFERRED EMBODIMENT

For the present invention, curing is defined as thermal processing, which includes reducing a metal compound contained within a thin film on a low-temperature substrate. A thin film is defined as a coating of less than 100 microns thick. Examples of low-temperature substrates include paper, plastic or polymer.

The present invention is a method for providing activation energy to perform a reduction-oxidation reaction in a thin film using intense pulsed light. The redox reaction may be the reduction of a metal oxide by an organic compound and may be performed on a low-temperature substrate.

Referring now to the drawings and in particular to Figure 1, there is depicted a flow diagram of a method for curing a thin film on a low-temperature substrate, in accordance with a preferred embodiment of the present invention. Starting in block 100, a non-conducting metal oxide is dispersed in a liquid, such as water, using any number of common dispersing agents such as polyvinylpyrrolidone or polystyrene-acrylate copolymers, as shown in block 110. The dispersion also includes at least one reducing agent. The reducing agent may be any of a number of compounds including alcohols, aldehydes, carboxylic acids and carbon black. Reducing agents preferably include glycerol, ascorbic acid, 1,2-hexanediol and glutaric acid. Other additives may include various surfactants for surface wetting, humectants, co-solvents, and binder resins. The dispersion may include conducting particles such as silver, copper, or gold. The dispersion may also contain partially oxidized metal particles. The non-conducting metal oxide can be any metal oxide listed in Table I.

**Table I**

MoO <sub>2</sub> , MoO <sub>3</sub>	molybdenum oxide
WO <sub>2</sub> , WO <sub>3</sub>	tungsten oxide
ReO <sub>2</sub> , Re <sub>2</sub> O <sub>5</sub> , ReO <sub>3</sub>	rhenium oxide
FeO, Fe <sub>2</sub> O <sub>3</sub>	iron oxide
RuO <sub>2</sub>	ruthenium oxide
OsO <sub>2</sub>	osmium oxide
CoO, Co <sub>3</sub> O <sub>4</sub>	cobalt oxide
Rh <sub>2</sub> O <sub>3</sub> , RhO <sub>2</sub>	rhodium oxide
IrO <sub>2</sub>	iridium oxide
NiO	nickel oxide
PdO	palladium oxide
PtO <sub>2</sub>	platinum oxide
Cu <sub>2</sub> O, CuO	copper oxide
Ag <sub>2</sub> O	silver oxide
Au <sub>2</sub> O <sub>3</sub>	gold oxide
ZnO	zinc oxide
CdO	cadmium oxide
In <sub>2</sub> O <sub>3</sub>	indium oxide
GeO, GeO <sub>2</sub>	germanium oxide
SnO, SnO <sub>2</sub>	tin oxide
PbO, PbO <sub>2</sub>	lead oxide
Sb <sub>2</sub> O <sub>3</sub> , Sb <sub>2</sub> O <sub>4</sub> , Sb <sub>2</sub> O <sub>5</sub>	antimony oxide
Bi <sub>2</sub> O <sub>3</sub>	bismuth oxide

The dispersion is then deposited on a low-temperature substrate as a thin film, as depicted in block **120**. The low-temperature substrate can be polymer (polyimide, polyethylene terephthalate, polyethylene naphthalate, polyethylene, polycarbonate, polystyrene, polyvinyl chloride, etc.), paper, etc. The dispersion may be deposited on a low-temperature substrate by any common printing technique including inkjet, gravure, flexographic, rollcoating, screen-printing and the like. Conversely, the non-conducting metal oxide and reducer (i.e., reducing agent) may be deposited on a low-temperature substrate as a thin film using a dry deposition process such as xerography.

The thin film along with the low-temperature substrate are subsequently exposed to a pulsed electromagnetic emission in order to initiate a redox reaction between the non-conducting metal oxide and reducer on the low-temperature substrate, as shown in block **130**. The pulsed electromagnetic source can be a laser, flash lamp, directed plasma arc lamp, microwave, or radiofrequency induction heater capable of delivering a pulse

length of less than 20 ms. An alternative embodiment is the use of an electron beam or intense arc lamp to deposit heat into the film to initiate the redox reaction as the film is being conveyed past the source of radiation. For the electron beam and arc lamp sources, the combination of a moving substrate and a static source has the effect of providing pulsed heating of the film. The electromagnetic source should have an emission greater than 500 W/cm<sup>2</sup>. As a result of the exposure, the thin film is rendered electrically conductive after the redox reaction.

Preferably, the thin film is cured while the low-temperature substrate is being conveyed past the light source using an automated curing apparatus as described below.

With reference now to Figure 2, there is illustrated a diagram of a curing apparatus for curing thin films on low-temperature substrates, in accordance with a preferred embodiment of the present invention. As shown, a curing apparatus 200 includes a conveyor system 210, a strobe head 220, a relay rack 230 and a reel-to-reel feeding system 240. Curing apparatus 200 is capable of curing a thin film 202 mounted on a low-temperature substrate 203 situated on a web being conveying past strobe head 220 at a relatively high speed. Conveyor system 210 can preferably operate at speeds from 2 to 1000 feet/min to move substrate 203. Curing apparatus 200 can preferably accommodate a web width of any width in 6-inch increments. Thin film 202 can be added on substrate 203 by one or combinations of existing technologies such as screen-printing, inkjet printing, gravure, laser printing, xerography, pad printing, painting, dip-pen, syringe, airbrush, flexographic, CVD, PECVD, evaporation, sputtering, etc. The deposition of thin film 202 onto substrate 203 may be performed inline with the curing process.

Strobe head 220, which is preferably water cooled, includes a high-intensity pulsed xenon flash lamp 221 for curing thin film 202 located on substrate 203. Pulsed xenon flash lamp 221 can provide pulses of different intensity, pulse length, and pulse repetition frequency. For example, pulsed xenon lamp 221 can provide 10  $\mu$ s to 10 ms pulses with a 3" by 6" wide footprint at a pulse repetition rate of up to 1 kHz. The spectral

content of the emissions from pulsed xenon flash lamp **221** ranges from 200 nm to 2,500 nm. The spectrum can be adjusted by replacing the quartz lamp with a cerium doped quartz lamp to remove most of the emission below 350 nm. The quartz lamp can also be replaced with a sapphire lamp to extend the emission from approximately 140 nm to approximately 4,500 nm. Filters may also be added to remove other portions of the spectrum. Flash lamp **221** can also be a water wall flash lamp that is sometimes referred to as a Directed Plasma Arc (DPA) lamp.

Relay rack **230** includes an adjustable power supply, a conveyance control module, and a strobe control module. The adjustable power supply can produce pulses with an energy of up to 4 kilojoules per pulse. Adjustable power supply is connected to pulsed xenon flash lamp **221**, and the intensity of the emission from pulsed xenon flash lamp **221** can be varied by controlling the amount of current passing through pulsed xenon flash lamp **221**.

The adjustable power supply controls the emission intensity of pulsed xenon flash lamp **221**. The power, pulse duration and pulse repetition frequency of the emission from pulsed xenon flash lamp **221** are electronically adjusted and synchronized to the web speed to allow optimum curing of thin film **202** without damaging substrate **203**, depending on the optical, thermal and geometric properties of thin film **202** and substrate **203**.

During the curing operation, substrate **203** as well as thin film **202** are being moved by conveyor system **210**. Conveyor system **210** moves thin film **202** under strobe head **220** where thin film **202** is cured by rapid pulses from pulsed xenon flash lamp **221**. The power, duration and repetition rate of the emissions from pulsed xenon flash lamp **221** are controlled by strobe control module, and the speed at which substrate **203** is being moved past strobe head **220** is determined by conveyor control module.

A sensor **250**, which can be mechanical, electrical, or optical, is utilized to sense the speed of conveyor system **210**. For example, the conveyor belt speed of conveyor

belt system **210** can be sensed by detecting a signal from a shaft encoder connected to a wheel that makes contact with the moving conveyor belt. In turn, the pulse repetition rate can be synchronized with the conveyor belt speed of conveyor belt system **210**. The synchronization of the strobe pulse rate  $f$  is given by:

$$f = 0.2 * s * o / w$$

where  $s$  = web speed [ft/min]

$o$  = overlap factor

$w$  = curing head width [in]

Overlap factor is the average number of strobe pulses that are received by a substrate at any one location. For example, with a web speed of 200 ft/min, an overlap factor of 5, and a curing head width of 2.75 inches, the pulse rate of the strobe is 72.7 Hz.

When flash lamp **221** is pulsed, thin film **202** is momentarily heated to provide activation energy for a redox reaction. When a rapid pulse train is combined with moving substrate **203**, a uniform cure can be attained over an arbitrarily large area as each section of thin film **202** may be exposed to multiple pulses, which approximates a continuous curing system such as an oven.

Unlike the prior art, in which reducers or fluxes have been introduced to remove oxide from metal particles before curing, the method of the present invention places a reducer directly in a thin film along with the oxide to be reduced by an intense pulsed light. The process can be performed in air because the requirement of an inert or reducing environment is obviated by the brief time of the reaction. Basically, the thin film is heated briefly to a high enough temperature in order for the reducer and the oxide to react, but the time of the reaction is brief enough to prevent significant chemical reaction with the air.

As a result of the intense pulsed light, the metal oxide is reduced by the reducer in the film resulting in a thin film of metal. Although the radiated power per unit area from the pulsed light source is very high ( $\sim 2 \text{ KW/cm}^2$ ), the pulse duration is so short that little energy ( $\sim 2 \text{ J/cm}^2$ ) is deposited on substrate **203**. Hence, substrate **203** is undamaged. Thus, the method of present invention allows a high-temperature redox reaction to occur on a thermally fragile substrate such as a plastic or paper. The process happens so quickly that oxidation of the metal in air is minimal, so an inert or reducing atmosphere is not needed. In addition to reducing the metal oxide, the intense pulsed light has the added benefit of sintering the metal particles to form a highly conductive trace without damaging the substrate. Both the reduction and the sintering appear to happen from each pulse of light.

As an alternative embodiment, the reducer is a metal with a negative reduction potential, such as aluminum, magnesium, or lithium. This allows the reduction of materials that do not have a positive reduction potential. The reducing metal may be in particulate or film form.

As another alternative embodiment, a method for cleaning or reacting with a surface is performed by depositing a reacting film on a surface and exposing the film to an intense pulsed light to react the film with the surface. In short, a relatively innocuous chemical heated to a very high temperature can have a similar chemical activity as a relatively dangerous one at room temperature. Applications include cleaning agents, surface preparation, etc. Since a relatively innocuous agent is only very active at high temperature, this means that a safer, and potentially more environmental cleaning agent can be used in place of a more dangerous one. Storage of such an agent is safer, and disposal of the agent after use is more inexpensive and environmental.

The following paragraph illustrates what is happening to a thin film during the process of the present invention. A typical thickness of a thin film is 1 micron, and the typical thickness of a substrate is 150 microns (6 mils). A preferred pulse on a copper

oxide/organic reducer based films is 330 V with a 1,000 microsecond pulse length. This setting corresponds to a radiant exposure of  $1.7 \text{ J/cm}^2$  or an average radiated power of  $1.7 \text{ KW/cm}^2$ . Ignoring the radiation losses, energy absorbed by evaporation of solvent, energy absorbed by melting of the PET at the interface of the thin film, and energy liberated from the redox reaction being performed a thermal simulation of the system assuming natural convection losses at the interfaces. Assuming the curing apparatus from Figure 2 is at room temperature ( $25^\circ\text{C}$ ) before the pulse, the calculated the peak temperature of the thin film at the end of the 1 ms pulse is about  $1,040^\circ\text{C}$ . The entire film/substrate returned to below the published  $150^\circ\text{C}$  decomposition temperature of PET within 25 ms. This heating is performed with no apparent damage to the substrate. However, unlike a typical convection oven set at the published decomposition temperature of PET, the considerably higher peak temperature provides ample activation energy for the redox reaction to occur. Since the redox reaction is certainly completed in a time frame shorter than 25 ms, there is not adequate time for the copper to be oxidized by the air. Hence, the redox reaction occurs and oxidation of the copper does not. Thus, a highly conductive copper film is created. Also, given the temperature that the thin film reaches, the resulting copper particles are also sintered by the pulse of light. The sintering has the effect of increasing both the electrical conductivity and stability of the film.

One advantage of the method of the present invention is that the reduction can be completed very rapidly, which makes it compatible with high-speed printing and web handling techniques. As a result, high temperature processing can be performed on inexpensive, low temperature substrates such as paper, plastic, or polymer. Another advantage of the method of the present invention is that the reduction can be performed in an ambient environment such as air. A further advantage of the method of the present invention is that copper, oxidized copper, or even copper oxide can be deposited on substrates and cured to resistivities rivaling printed silver at a cost dramatically lower than silver. More specifically, copper oxidizes when it is heated in air. This invention allows the curing of copper particles hi air rendering a highly conductive film regardless of their level of oxidation.

As has been described, the present invention provides a method for rapidly reducing thin films on low-temperature substrates.

## EXAMPLES

### Example 1 - Ascorbic acid reducer

A copper oxide dispersion was produced by mixing 3.0g <50nm copper (II) oxide, 3.6g deionized water, 0.15g PVP K-30, 0.3g ethylene glycol, 0.04g Tergitol<sup>®</sup> TMN-6, 0.02g Dynol<sup>®</sup> 604, 0.02g BYK<sup>®</sup>-020, and 0.66g ascorbic acid in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 1,000 microseconds, and overlap factor of 2 at 24 feet per minute in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

### Example 2 - Ethylene glycol/glycerol reducer

A copper oxide dispersion was produced by mixing 2.0g NanoArc<sup>®</sup> copper oxide, 5.7g deionized water, 0.10g PVP K-30, 0.6g ethylene glycol, 0.03g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 0.32g glycerol in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 850 microseconds, and overlap factor of 2 at 24 feet per minute in an air environment. Although the film was not

electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 3 - Ethylene glycol/glycerol reducer

A copper oxide dispersion was produced by mixing 2.0g NanoArc<sup>®</sup> copper oxide, 5.4g deionized water, 0.10g PVP K-30, 0.6g ethylene glycol, 0.03g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 0.67g glycerol in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 1,000 microseconds, and overlap factor of 3 at 24 feet per minute in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 4 - Ethylene glycol/glycerol reducer

A copper oxide dispersion was produced by mixing 2.0g NanoArc<sup>®</sup> copper oxide, 4.9g deionized water, 0.10g PVP K-30, 0.5g ethylene glycol, 0.03g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 1.32g glycerol in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a single pulse at 750V with a pulse length of 2,300 in an air environment. The color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper. The sheet resistance of the film was 4.1  $\Omega$ /sq.

#### Example 5 - glucose reducer

A copper oxide dispersion was produced by mixing 1.75g NanoArc<sup>®</sup> copper oxide, 5.3g deionized water, 0.09g PVP K-30, 0.6g ethylene glycol, 0.02g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 0.79g glucose in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar. Separately, the dispersion was applied to a sheet of Epson Photo Paper by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 400 microseconds, and overlap factor of 2 at 24 feet per minute for three passes in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 6 - Glucose reducer

A copper oxide dispersion was produced by mixing 1.75g NanoArc<sup>®</sup> copper oxide, 5.3g deionized water, 0.09g PVP K-30, 0.6g ethylene glycol, 0.02g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 1.59g glucose in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 500 microseconds, and overlap factor of 2 at 24 feet per minute in an air environment. The color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper. The sheet resistance of the film was 2.2  $\Omega$ /sq.

#### Example 7 - Hexanediol reducer

A copper oxide dispersion was produced by mixing 1.5g NanoArc<sup>®</sup> copper oxide, 7.5g deionized water, 0.08g PVP K-30, 0.8g ethylene glycol, 0.03g Tergitol<sup>®</sup> TMN-6, 0.02g Dynol<sup>®</sup> 604, and 0.47g 1,2-hexanediol in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 600 microseconds, and overlap factor of 2 at 24 feet per minute in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 8 - Glutaric acid reducer

A copper oxide dispersion was produced by mixing 1.5g <50nm copper (II) oxide, 6.8g deionized water, 0.08g PVP K-30, 0.8g ethylene glycol, 0.03g Tergitol<sup>®</sup> TMN-6, 0.02g Dynol<sup>®</sup> 604, and 0.47g glutaric acid in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 1,200 microseconds, and overlap factor of 3 at 25 feet per minute in an air environment. The color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper. The sheet resistance of the film was 2.7  $\Omega$ /sq.

#### Example 9 - Polyacrylamide reducer

A copper oxide dispersion was produced by mixing 1.75g NanoArc<sup>®</sup> copper oxide, 5.3g deionized water, 0.09g PVP K-30, 0.6g ethylene glycol, 0.02g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 1.25g polyacrylamide in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 800 microseconds, and overlap factor of 2 at 24 feet per minute in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 10 - Pentaerythritol reducer

A copper oxide dispersion was produced by mixing 1.75g NanoArc<sup>®</sup> copper oxide, 5.3g deionized water, 0.09g PVP K-30, 0.6g ethylene glycol, 0.02g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 0.90g pentaerythritol in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 600 microseconds, and overlap factor of 2 at 24 feet per minute in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 11 - Succinic acid reducer

A copper oxide dispersion was produced by mixing 1.75g NanoArc<sup>®</sup> copper oxide, 5.3g deionized water, 0.09g PVP K-30, 0.6g ethylene glycol, 0.02g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 0.71g succinic acid (sodium salt) in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 700 microseconds, and overlap factor of 4 at 24 feet per minute in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 12 - Carbon reducer

A copper oxide dispersion was produced by mixing 1.75g NanoArc<sup>®</sup> copper oxide, 5.3g deionized water, 0.09g PVP K-30, 0.6g ethylene glycol, 0.02g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 0.32g carbon black in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 500 microseconds, and overlap factor of 2 at 24 feet per minute for four passes in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 13 - Uric acid reducer

A copper oxide dispersion was produced by mixing 1.75g NanoArc<sup>®</sup> copper oxide, 5.3g deionized water, 0.09g PVP K-30, 0.6g ethylene glycol, 0.02g Tergitol<sup>®</sup> TMN-6, 0.01g Dynol<sup>®</sup> 604, and 0.89g uric acid in a 20mL vial. 5g of zirconium oxide milling media was added and the vial was agitated for 60 minutes.

The dispersion was applied to a sheet of Melinex<sup>®</sup> ST505 PET by drawdown using a #5 Meyer bar.

The sample was cured with a pulse length of 600 microseconds, and overlap factor of 2 at 24 feet per minute for four passes in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper.

#### Example 14 - Inkjet with glycerol reducer

A copper oxide dispersion was produced by first milling a mixture of 52.5g NanoArc<sup>®</sup> copper oxide, 2.6g PVP K-30, and 294.9g deionized water. The resulting average particle size was 115nm. An inkjet ink was produced by mixing 8.4g of the milled copper oxide dispersion, 1.0g glycerol, 0.5g ethylene glycol, 0.04g Triton<sup>®</sup> X-100, and 0.03g BYK<sup>®</sup>-020.

The inkjet ink was printed using a desktop inkjet printer onto Pictorico brand PET.

The sample was cured with a pulse length of 300 microseconds, and overlap factor of 2 at 24 feet per minute in an air environment. The color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper. The sheet resistance of the film was 1  $\Omega$ /sq.

Example 15 - Copper powder with ascorbic acid and glycerol reducer

A copper dispersion was produced by mixing 2.5g of Mitsui copper powder, 0.04g of BYK<sup>®</sup>-020, 0.04g of Tergitol<sup>®</sup> TMN-6, 0.25g of PVP K-30, 0.89g of glycerol, 0.45g of ethylene glycol, 0.76g of ascorbic acid in 7.57g of deionized water.

The dispersion was applied to a sheet of Pictorico brand PET by drawdown using a #10 Meyer bar.

The sample was cured with a pulse length of 1,000 microseconds, and overlap factor of 4 at 24 feet per minute in an air environment. The color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper. The sheet resistance of the film was 40 m $\Omega$ /sq. Assuming the film was fully dense, it was 1.3 microns thick and thus had a bulk conductivity of 5.2 micro  $\Omega$ -cm or 3.0 times the bulk resistivity of pure copper.

Example 16 - Inkjet with ascorbic acid reducer

A copper oxide dispersion was produced by first milling a mixture of 52.5g NanoArc<sup>®</sup> copper oxide, 2.6g PVP K-30, and 294.9g deionized water. The resulting average particle size was 115nm. A first inkjet ink was produced by mixing 8.4g of the milled copper oxide dispersion, 1.0g glycerol, 0.5g ethylene glycol, 0.04g Triton<sup>®</sup> X-100, and 0.03g BYK<sup>®</sup>-020. A second inkjet ink was produced by mixing 0.1g of BYK<sup>®</sup>-020, 0.2g of Triton<sup>®</sup> X-100, 10.0 g of ascorbic acid, 3.0g of ethylene glycol, 4.5g of glycerol in 42.5g of deionized water.

Both inkjet inks were printed sequentially using an inkjet printer onto Pictorico brand PET.

The sample was cured with a pulse length of 1,000 microseconds, and overlap factor of 1 at 24 feet per minute in an air environment. The color of the film changed from dark brown to a copper color indicating significant conversion of the copper

oxide to copper. The film was estimated to be 0.3 micron thick and had a sheet resistance of 140mΩ/sq indicating a bulk conductivity of 4.1 micro Ω-cm or 2.4 times the bulk resistivity of pure copper.

All of the above-mentioned examples were prepared identically and placed in an oven containing an air environment at 150°C for 30 minutes. In all cases, there was no visual evidence of conversion or conductivity of the film. Higher oven temperatures were not possible since the highest working temperature of PET is 150°C. When higher temperature substrates, such as Kaptan™ or glass were used, no conversion was seen even at temperatures up to 800°C.

#### Example 17 - Copper sulphate with ascorbic acid reducer

A first solution was made with 20wt%CuSO<sub>4</sub>·5H<sub>2</sub>O in deionized water. A second solution was produced by mixing 0.1 g of BYK®-020, 0.2 g of Triton® X-100, 10.0 g of ascorbic acid, 3.0 g of ethylene glycol, 4.5 g of glycerol in 42.5 g of deionized water.

The first solution was deposited on ordinary photocopy paper by drawdown using a #10 Meyer bar. This was followed by a deposition of the second solution by drawdown using a #5 bar.

The sample was cured with a pulse length of 1,000 microseconds, and overlap factor of 4 at 24 feet per minute for three passes in an air environment. Although the film was not electrically conductive, the color of the film changed from dark brown to a copper color indicating significant conversion of the copper oxide to copper. Under a low magnification microscope it was observed that the copper coated the fibers of the paper.

#### Example 18 - Aluminum reducer

A dispersion was made with 0.29g of Valimet™-H2 aluminum powder, 0.77g of <5micron copper (II) oxide from Sigma- Aldrich, 0.1 Ig of PVP K-30 in 6.0g of deionized water.

The dispersion was applied to a sheet of Pictorico brand PET by drawdown using a #10 Meyer bar.

The sample was cured with a pulse length of 1,000 microseconds, and overlap factor of 2 at 28 feet per minute in an air environment. Although the film was not electrically conductive, the film converted from a dark brown to a copper color.

In contrast, identical films were prepared in all of the above examples were placed in an oven containing an air atmosphere at 150°C for 30 minutes. 150°C was chosen since it is the highest working temperature for PET. No conversion was observed, and no films had any measurable electrical resistance (greater than 400 MΩ/square).

While the invention has been particularly shown and described with reference to a preferred embodiment, it will be understood by those skilled in the art that various changes in form and detail may be made therein.

## CLAIMS

What is claimed is:

1. A method for producing an electrically conductive thin film on a substrate, said method comprising:
  - dispersing copper powder, ascorbic acid and glycerol in a liquid;
  - depositing said dispersion on a non-conductive substrate as a thin film; and
  - exposing said thin film along with said substrate to a pulsed electromagnetic emission in an ambient atmosphere to chemically react said copper powder and said ascorbic acid and glycerol to render said thin film electrically conductive.
  
2. A method for reducing thin films on low-temperature substrates, said method comprising:
  - dispersing copper sulphate in a first liquid;
  - dispersing ascorbic acid and glycerol in a second liquid;
  - depositing said first and second dispersions on a non-conductive substrate as a thin film;and
  - exposing said thin film along with said substrate to a pulsed electromagnetic emission in an ambient atmosphere in order to initiate a redox reaction between said copper sulphate and said ascorbic acid and glycerol on said substrate.
  
3. The method of Claim 1 or 2, wherein said substrate is paper.
  
4. The method of Claim 3, wherein said paper is coated with an ink receiving layer.
  
5. The method of Claim 1 or 2, wherein said substrate is a polymer.
  
6. The method of Claim 1 or 2, wherein said polymer is coated with an ink receiving layer.

7. The method of Claim 1 or 2, wherein said pulsed electromagnetic emission is generated by any one of a laser, a flash lamp, a directed plasma arc lamp, microwave, a radio-frequency induction heater, an electron beam, and an arc lamp.
8. The method of Claim 1, wherein said liquid is water.
9. The method of Claim 1 or 2, wherein said depositing is performed by printing.
10. The method of Claim 1 or 2, wherein said pulsed electromagnetic emission has a pulse length of less than 20 ms.
11. The method of Claim 1 or 2, wherein said pulsed electromagnetic emission is greater than 500 W/cm<sup>2</sup>.

1 / 1




FIG. 1




FIG. 2

START

DISPERSE A REDUCIBLE METAL COMPOUND  
AND A REDUCING AGENT IN A LIQUID

110

DEPOSIT DISPERSION ON A LOW-TEMPERATURE  
SUBSTRATE AS A THIN FILM

120

EXPOSE THIN FILM AND LOW-TEMPERATURE  
SUBSTRATE TO A PULSED ELECTROMAGNETIC EMISSION

130